

表1. 厚さ t0.05 ~ t0.18 焼入れリボン鋼 (SK焼入鋼帯) の
定尺サイズ表: QSK2 (SK-2)、QSK4 (SK-4)

鋼種 記号	厚さ mm	幅 mm	厚さの 許容差 (自主規格) mm	厚さの 許容差 (JIS) mm	単位重量 kg/m	硬度 (硬さ) HV	表面 仕上げ
QSK2 (SK-2)	0.05	20	± 0.005	± 0.008	0.0079	530 ~ 570	研磨青
	0.05	30	± 0.005	± 0.008	0.0118	530 ~ 570	研磨青
	0.08	38	± 0.005	± 0.008	0.0239	530 ~ 570	研磨青
QSK4 (SK-4)	0.1	3	± 0.006	± 0.010	0.0024	490 ~ 530	研磨青
	0.1	8	± 0.006	± 0.010	0.0063	490 ~ 530	研磨青
	0.1	16	± 0.006	± 0.010	0.0126	490 ~ 530	研磨青
	0.1	19	± 0.006	± 0.010	0.0149	490 ~ 530	研磨青
	0.1	25	± 0.006	± 0.010	0.0196	490 ~ 530	研磨青
	0.1	32	± 0.006	± 0.010	0.0251	490 ~ 530	研磨青
	0.1	35	± 0.006	± 0.010	0.0275	490 ~ 530	研磨青
	0.1	50	± 0.006	± 0.010	0.0393	530 ~ 570	研磨青
	0.1	75	± 0.006	± 0.010	0.0589	530 ~ 570	研磨青
	0.1	102	± 0.006	± 0.010	0.0801	490 ~ 530	研磨青
	0.15	6	± 0.007	± 0.015	0.0071	490 ~ 530	研磨青
	0.15	8	± 0.007	± 0.015	0.0094	490 ~ 530	研磨青
	0.15	10	± 0.007	± 0.015	0.0118	490 ~ 530	研磨青
	0.15	13	± 0.007	± 0.015	0.0153	490 ~ 530	研磨青
	0.15	20	± 0.007	± 0.015	0.0236	490 ~ 530	研磨青
	0.15	25	± 0.007	± 0.015	0.0294	490 ~ 530	研磨青
	0.15	30	± 0.007	± 0.015	0.0353	490 ~ 530	研磨青
	0.15	50	± 0.007	± 0.015	0.0589	510 ~ 540	研磨青
	0.15	75	± 0.007	± 0.015	0.0883	530 ~ 570	研磨青
	0.15	102	± 0.007	± 0.015	0.1201	490 ~ 530	研磨青
0.18	75	± 0.007	± 0.015	0.1060	490 ~ 530	研磨青	