

表3. 厚さ t0.35 ~ t0.5 焼入れリボン鋼 (SK焼入鋼帯) の
定尺サイズ表: QSK5 (SK-5)

鋼種 記号	厚さ mm	幅 mm	厚さの 許容差 (自主規格) mm	厚さの 許容差 (JIS) mm	単位重量 kg/m	硬度 (硬さ) HV	表面 仕上げ
QSK5 (SK-5)	0.35	8	±0.013	±0.020	0.0220	490 ~ 530	研磨青
	0.35	10	±0.013	±0.020	0.0275	490 ~ 530	研磨青
	0.35	16	±0.013	±0.020	0.0440	490 ~ 530	研磨青
	0.35	19	±0.013	±0.020	0.0522	490 ~ 530	研磨青
	0.35	30	±0.013	±0.020	0.0824	490 ~ 530	研磨青
	0.35	102	±0.013	±0.020	0.2802	490 ~ 530	研磨青
	0.4	5	±0.013	±0.025	0.0157	490 ~ 530	研磨青
	0.4	6	±0.013	±0.025	0.0188	490 ~ 530	研磨青
	0.4	8	±0.013	±0.025	0.0251	490 ~ 530	研磨青
	0.4	10	±0.013	±0.025	0.0314	490 ~ 530	研磨青
	0.4	13	±0.013	±0.025	0.0408	490 ~ 530	研磨青
	0.4	16	±0.013	±0.025	0.0502	490 ~ 530	研磨青
	0.4	19	±0.013	±0.025	0.0597	490 ~ 530	研磨青
	0.4	25	±0.013	±0.025	0.0785	490 ~ 530	研磨青
	0.4	30	±0.013	±0.025	0.0942	490 ~ 530	研磨青
	0.4	40	±0.013	±0.025	0.1256	490 ~ 530	研磨青
	0.4	50	±0.013	±0.025	0.1570	490 ~ 530	研磨青
	0.4	75	±0.013	±0.025	0.2355	490 ~ 530	研磨青
	0.4	102	±0.013	±0.025	0.3203	490 ~ 530	研磨青
	0.45	19	±0.013	±0.025	0.0671	490 ~ 530	研磨青
	0.45	25	±0.013	±0.025	0.0883	490 ~ 530	研磨青
	0.45	102	±0.013	±0.025	0.3603	490 ~ 530	研磨青
	0.5	5	±0.015	±0.025	0.0196	480 ~ 520	研磨青
	0.5	6	±0.015	±0.025	0.0236	480 ~ 520	研磨青
	0.5	7	±0.015	±0.025	0.0275	480 ~ 520	研磨青
	0.5	8	±0.015	±0.025	0.0314	480 ~ 520	研磨青
	0.5	10	±0.015	±0.025	0.0393	480 ~ 520	研磨青
	0.5	13	±0.015	±0.025	0.0510	480 ~ 520	研磨青
	0.5	16	±0.015	±0.025	0.0628	480 ~ 520	研磨青
	0.5	19	±0.015	±0.025	0.0746	480 ~ 520	研磨青
	0.5	22	±0.015	±0.025	0.0864	480 ~ 520	研磨青
	0.5	25	±0.015	±0.025	0.0981	480 ~ 520	研磨青
	0.5	30	±0.015	±0.025	0.1178	480 ~ 520	研磨青
	0.5	32	±0.015	±0.025	0.1256	480 ~ 520	研磨青
	0.5	35	±0.015	±0.025	0.1374	480 ~ 520	研磨青
	0.5	50	±0.015	±0.025	0.1963	480 ~ 520	研磨青
	0.5	60	±0.015	±0.025	0.2355	480 ~ 520	研磨青
	0.5	75	±0.015	±0.025	0.2944	480 ~ 520	研磨青
	0.5	102	±0.015	±0.025	0.4004	480 ~ 520	研磨青