

表4 . 厚さ t0.6~t1.0 焼入れリボン鋼(SK焼入鋼帯)の
定尺サイズ表:QSK5(SK-5)

鋼種 記号	厚さ mm	幅 mm	厚さの 許容差 (自主規格) mm	厚さの 許容差 (JIS) mm	単位重量 kg/m	硬度 (硬さ) HV	表面 仕上げ
QSK5 (SK-5)	0.6	8	±0.017	±0.030	0.0377	480~520	研磨青
	0.6	16	±0.017	±0.030	0.0754	480~520	研磨青
	0.6	19	±0.017	±0.030	0.0895	480~520	研磨青
	0.6	25	±0.017	±0.030	0.1178	480~520	研磨青
	0.6	30	±0.017	±0.030	0.1413	480~520	研磨青
	0.6	50	±0.017	±0.030	0.2355	480~520	研磨青
	0.6	102	±0.017	±0.030	0.4804	480~520	研磨青
	0.7	102	±0.017	±0.030	0.5605	480~520	研磨青
	0.8	5	±0.020	±0.030	0.0314	480~520	研磨青
	0.8	10	±0.020	±0.030	0.0628	480~520	研磨青
	0.8	13	±0.020	±0.030	0.0816	480~520	研磨青
	0.8	16	±0.020	±0.030	0.1005	480~520	研磨青
	0.8	19	±0.020	±0.030	0.1193	480~520	研磨青
	0.8	25	±0.020	±0.030	0.1570	480~520	研磨青
	0.8	50	±0.020	±0.030	0.3140	480~520	研磨青
	0.8	102	±0.020	±0.030	0.6406	480~520	研磨青
	0.9	102	±0.025	±0.040	0.7206	480~520	研磨青
	1.0	10	±0.025	±0.040	0.0785	480~520	研磨青
	1.0	14	±0.025	±0.040	0.1099	480~520	研磨青
	1.0	16	±0.025	±0.040	0.1256	480~520	研磨青
	1.0	19	±0.025	±0.040	0.1492	480~520	研磨青
	1.0	25	±0.025	±0.040	0.1963	480~520	研磨青
	1.0	30	±0.025	±0.040	0.2355	480~520	研磨青
	1.0	32	±0.025	±0.040	0.2512	480~520	研磨青
1.0	50	±0.025	±0.040	0.3925	480~520	研磨青	
1.0	102	±0.025	±0.040	0.8007	480~520	研磨青	